



# Phycosynthesis of silver nanoparticles from extract of *Gracilaria foliifera* (Forsskal) Boergesen

**K. SIVAKUMAR**

Division of algal Biotechnology, Department of Botany  
Annamalai University, Annamalainagar - 608 002, Tamil Nadu  
E-mail : kshivam69@gmail.com

## ABSTRACT

The synthesis, characterization and application of biologically synthesized nanomaterials are an innovative, cheaper and environmental friendly and require less-labor. The present study deals with the synthesis of silver nanoparticles (Ag-NPs) using the aqueous extract of red seaweed *Gracilaria foliifera* extract. The complete reduction of silver ions was observed after 72 h of reaction at 300°C under shaking conditions. The colour changes in reaction mixture (pale yellow to reddish brown) was observed during the incubation period, because of the formation of silver nanoparticles in the reaction mixture enables to produce particular colour due to their specific properties. The formation of Ag-NPs confirmed by UV Visible Spectroscopy clearly indicates the interaction between silver ions and biomolecules present in the aqueous seaweed extract. The X-Ray Diffraction (XRD) pattern showed crystalline nature of silver nanoparticles, Scanning Electron Microscopy (SEM) with EDS analysis patterns showed the synthesized of Ag-NPs were predominantly spherical in shape and polydispersed. Fourier Transform Infra-Red (FT-IR) spectroscopy analysis showed that the synthesized nano-Ag was capped with bimolecular compounds which are responsible for reduction of silver ions. The approach of plant-mediated synthesis appears to be cost efficient, eco-friendly and easy alternative to conventional methods of silver nanoparticles synthesis.

## Introduction

Nanoparticles with controlled size and composition are of fundamental and technological interest as they provide solutions to technological and environmental challenges in the areas of solar energy conversion, catalysis, medicine and water treatment. Thus, production and application of nanomaterials from 1 to 100 nanometers (nm) is an emerging field of research (Dahl *et al.*, 2007, Hutchison, 2008). Nanobiotechnology is a thrust area and currently there is a growing need to use environmental friendly nanoparticles that do not produce toxic wastes in their process synthesis protocol. To achieve this, it is essential to begin synthesis processes, which happen to be mostly of biological nature (Mansoori, 2005).

Biological synthesized nanoparticles can have good control on the size distribution than the other methods. Nanoparticles could also be stabilized directly in the process by protein (Duran *et al.*, 2005). Biomolecules as reducing agents are found to have a significant advantage over their

counterparts as protecting agents (Huang *et al.*, 2007). To date, metallic nanoparticles are mostly prepared from noble metals. Silver (Ag) is the metal of choice in the field of biological systems, living organisms and medicine (Parashar *et al.*, 2009). Silver nanoparticles have an advantage over other metal nanoparticles (e.g. gold and copper) because the surface plasmon resonance energy of Ag is located far from the interband transition energy. Biosynthesis of nanoparticles by plant extracts is currently under exploitation. The biosynthesis of gold and silver nanoparticles using seaweed *Sargassum wightii* have been achieved (Vigneshwaran *et al.*, 2007). Nanoparticles are classified primarily into two types viz organic and inorganic nanoparticles. The nanoparticles of carbon are called the organic nanoparticles. Magnetic nanoparticles, noble metal nanoparticles (platinum, gold and silver) and semiconductor nanoparticles (titanium dioxide, zinc oxide and zinc sulfide) are classified as inorganic nanoparticles (Kathiresan and Asmathunisha, 2013). Photocatalytic

degradation of methyl orange was measured spectrophotometrically by using silver as nanocyst under visible light illumination. The result revealed that biosynthesized silver nanoparticles using *Hypnea musciformis* was found to be impressive in degrading methyl orange was reported by Ganapathyselvam and Sivakumar (2014).

## Materials and Methods

### Screening and selection of plants

Fresh red seaweed of *Gracilaria foliifera* (Fig. 1 and 2) was collected from Pudumadam coastal region (9.2770° N, 78.9938° E), in Gulf of Mannar, Tamil Nadu, South India. Samples were brought to laboratory in polythene bags and cleaned thoroughly with fresh water to remove adhering debris and associated biota. The algae were cleaned using brush for the removal of the epiphytes with distilled water. After cleaning, the alga was dried in shade at room temperature for a week.

### Preparation of aqueous extract

The whole biomass of *Gracilaria foliifera* were initially rinsed thrice in distilled water and dried on paper toweling and samples (25 g) were cut into fine pieces and boiled with 100 ml



Fig. 1. Morphology of *Gracilaria foliifera*




Fig. 2. Scanning Electron Micrograph of Internal Structure of *Gracilaria foliifera*

of sterile distilled water for 5 min. The crude extract was passed through Whatman No.1 filter paper and the filtrate was stored at 4°C for further use.

### Synthesis of silver nanoparticles

Silver nitrate (AgNO<sub>3</sub>) of analytical grade (AR) was purchased from E. Merck (India). In the typical synthesis of silver nanoparticles, 10 ml of the aqueous extract of *Gracilaria foliifera* was added to 90 ml of 1 mM aqueous AgNO<sub>3</sub> solution in 250 ml conical flask and kept at room temperature for 72 h at 120 rpm. Controls were maintained throughout the experiments.

### UV-visible spectroscopy analysis

The colour change in reaction mixture (metal ion solution + seaweed extract) was recorded through visual observation. The bio reduction of silver ions in aqueous solution was monitored by periodic sampling of aliquots (0.5 ml) and subsequently measuring UV-Vis spectra of the solution. UV-vis spectra of these aliquots were monitored as a function of time of reaction on UV-Vis spectrophotometer UV-2450 (Shimadzu).

### FTIR measurement

To remove any free biomass residue or compound that is not the capping ligand of the nanoparticles, the residual solution of 100 ml after reaction was centrifuged at 5000 rpm for 10 min. The supernatant was again centrifuged at 10000 rpm for 60 min and the pellet was obtained. This is followed by redispersion of the pellet of Ag-NPs into 1 ml of deionized water. Thereafter, the purified suspension was freeze dried to obtain dried powder. Finally, the dried nanoparticles were analyzed by FTIR Nicolet Avatar 660 (Nicolet, USA).

### XRD measurement

The Ag-NPs solution thus obtained was purified by repeated centrifugation at 5000 rpm for 20 min followed by redispersion of the pellet of Ag-NPs in 10 ml of deionized water. After freeze drying of the purified Ag-NPs, the structure and composition were analyzed by XRD. The dried mixture of Ag-NPs was collected for the determination of the formation of Ag-NPs by an X'Pert Pro x-ray diffractometer (PAN analytical BV, The Netherlands) operated at a voltage of 40 kV and a current of 30 mA with Cu K $\alpha$  radiation in a  $\theta$  - 2  $\theta$  configuration. The crystallite domain size was calculated from the width of the XRD peaks, assuming that they are free from non-uniform strains, using the Scherrer's formula.

$$D = 0.94 \lambda / \beta \cos \theta$$

where D is the average crystallite domain size perpendicular to the reflecting planes,  $\beta$  is the X-ray wavelength,  $\theta$  is the full width at half maximum (FWHM) and  $\theta$  is the diffraction angle. To eliminate additional instrumental broadening the FWHM was corrected, using the FWHM from a large grained Si sample.

$$\beta_{\text{corrected}} = (\text{FWHM}_{\text{sample}} - \text{FWHM}_{\text{Si}})^2$$

This modified formula is valid only when the crystallite size is smaller than 100 nm (Cullity, 1978).

### SEM analysis of silver nanoparticles

Scanning Electron Microscopic (SEM) analysis was done using Hitachi S-4500 SEM machine. Thin films of the sample were prepared on a carbon coated copper grid by just dropping a very small amount of the sample on the grid, extra solution was removed using a blotting paper and then the film on the SEM grid were allowed to dry by putting it under a mercury lamp for 5 min.

## Results and Discussion

### Phyco-synthesis of Ag nanoparticles

The reduction of  $\text{AgNO}_3$  in aqueous seaweed extract by heating at  $60^\circ\text{C}$  showed visible colour change whereas no color change was observed in  $\text{Ag}^+$  solution as shown in Fig. 3. The colour of solution gradually intensified on heating, which indicates the synthesis of Ag nanoparticles. The change in colour is an attribute to excitation of surface plasmon vibrations of Ag nanoparticles (Mulvaney, 1996). Notably, even after 24 h there is no remarkable deepening of colour indicating the saturation of reaction (data not shown). This reflects that the particles may be well dispersed in the solution with mild agglomeration (Nabikhan *et al.*, 2010).

### UV-visible spectroscopy

UV-vis spectroscopy is a convenient, preliminary and indirect method for characterization of Ag nanoparticles based on optical properties called surface plasmon resonance (SPR) (Kuber and D'Souza, 2006). The color of the seaweed extract becomes turbid after the addition of aqueous  $\text{AgNO}_3$  solution signifying the initiation of reaction. The silver SPR band occurs at 420 nm with progressive increase in absorbance upon increasing time until 20 min as shown in Fig. 4. The observed band in this range has been associated with Ag nanoparticles confirming the synthesis of spherical Ag nanoparticles with narrow size distribution (Henglein, 1993; Kumar *et al.*, 2012). Elevation in temperature results in formation of spherical and octahedral shaped nanoparticles of size 5–200 nm (Lengke *et*



Fig. 3. Silver nitrate ( $\text{AgNO}_3$ ) solution and colour changes during the reduction of  $\text{AgNO}_3$  into AgNPs by the extract of *Gracilaria foliifera* after 24 h of incubation




Fig. 4. UV-visible absorption spectra of silver nanoparticles

*et al.*, 2007). Similarly, shape-controlled Ag nanoparticles can be also synthesized in biological route by varying temperature (Bansal *et al.*, 2012). Hence, a possible mechanism to control particle size and shape with reference to SPR peak has been addressed.

### FTIR spectrum

FTIR analysis was used for the characterization of the extract and the resulting nanoparticles. Absorbance bands seen at (3405.61), (2958.50), (2922.09 and 2851.91), (1639.40), (1528.93 and 1507.38), (1450.64 and 1383.23), (1228.82, 1158.34 and 1030.72) and (663.64)  $\text{cm}^{-1}$  were assigned to the NH stretching vibrations of free NH group, O-H Carboxylic acids broad stretching vibration, C-H Alkanes Strong stretching vibrations, N-H Amine medium bend,  $\text{NO}_2$  Nitro compounds stretching Asymmetrical bend, C-H Alkanes Scissoring and bending, C-N Amines medium stretching vibrations and C-H Alkynes broad bend vibrations of non-conjugated group and CH bending vibrations of  $\text{CH}_3$  group respectively (Fig. 5). The results revealed that the capping ligand of the Ag-NPs may be an aromatic compound or alkanes or amines. Several species of *Gracilaria* have been reported to contain abundant of amino acids, fatty acids, vitamins, minerals, phenolic compounds and carbohydrates (Yang *et al.*,




Fig. 5. FTIR spectra of silver nanoparticles synthesized by the reduction of 1mM silver nitrate with the *Gracilaria foliifera* extract




Fig. 6. XRD patterns of capped silver nanoparticles synthesized by treating *Gracilaria foliifera* extract with 1 mM silver nitrate

2012). Of which, phenolic compounds especially polyphenols and tannin were reported to have antimicrobial, anti-carcinogenic and anti-oxidant properties (Arunkumar *et al.*, 2010). Satyavani *et al.* (2011) reported that silver ions may possibly bind to phenolic compounds with one or more aromatic ring resulting in the formation of Ag nanoparticles.

#### XRD analysis

The biosynthesized silver nanostructure by using *Gracilaria foliifera* extract was further demonstrated and confirmed by the characteristic peaks observed in the XRD image at  $\theta = 28.09^\circ$ , marked with (220). The peaks matches with the Joint Committee on Powder Diffraction Standards (file No. 04-0783), which further proves the formation of crystal AgNPs (Swanson *et al.*, 1953). A number of Bragg reflections corresponding to the (220) sets of lattice planes were observed which may be indexed based on the face-centred crystal structure of silver. The XRD pattern thus clearly showed that the Ag-NPs are crystalline in nature (Fig. 6). The X-ray diffraction results clearly show that the AgNPs formed by the reduction of silver ions by the extract of *Gelidiella* sp. are crystalline in nature (Udayasoorian *et al.*, 2011).

#### Electron Microscopy Study (SEM)

The SEM image (Fig. 7) showing the high density Ag-NPs synthesized by the *Gracilaria foliifera* further confirmed the development of silver nanostructures. The SEM micrographs of nanoparticle obtained in the filtrate showed that Ag-NPs are spherical shaped, well distributed without aggregation in solution. Analysis through Energy dispersive X-ray (EDS) spectrometers confirmed the presence of elemental silver signal of the silver nanoparticles (Fig. 7). The optical absorption peak is observed at 3KeV, which is typical for the absorption of metallic AgNPs (Magudapathy *et al.*, 2001). The vertical axis displays the number of x-ray counts whilst the horizontal axis





Fig. 7. SEM micrograph of silver nanoparticles synthesized by the reaction of 1 mM silver nitrate with *Gracilaria foliifera* extract and Energy Dispersive Spectroscopy analysis

displays energy in KeV. Identification lines for the major emission energies for silver (Ag) are displayed and these correspond with peaks in the spectrum, thus giving confidence that silver has been correctly identified. Similar phenomenon was reported by Chandran *et al.* (2006). In the present work silver nanoparticles was successfully synthesized using *Gracilaria foliifera* extract. The silver nanoparticles were characterized by Scanning electron microscope. The SEM images revealed that the particles are spherical in shape and their size varied from 10-100nm. The XRD result confirmed that the particles have a face centered cubic crystalline structure. This is an efficient, eco-friendly and simple process.

#### References

- Arunkumar, K., S.R. Sivakumar and R. Rengasamy 2010. Review on bioactive potential in seaweeds (Marine Macroalgae): a special emphasis on biodiversity of seaweeds against plant pathogens. *Asian J. Plant. Sci.*, 9: 227–240.
- Bansal, V., A. Bharde, R. Ramanathan and S.K. Bhargava 2012. Inorganic materials using 'unusual' microorganisms. *Adv. Colloid Interface Sci.*, doi:10.1016/j.cis.2012.06.013.
- Chandran, S.P., M. Chaudhary, R. Pasricha, A. Ahmad and M. Sastry 2006. Synthesis of gold nanotriangles and silver nanoparticles using *Aloe vera* plant extract. *Biotechnol Prog.*, 22: 577.
- Dahl, J.A., B.L.S. Maddux and J.E. Hutchison 2007. Toward greener nanosynthesis. *Chemical Reviews*, 107: 2228–2269.

- Duarn, N., P.D. Marcato, O.L. Alves, G.I.H. Souza and E. Esposito 2005. Mechanistic aspects of biosynthesis of silver nanoparticles by several *Fusarium oxysporum* strains. *J. Nanobiotechnol.*, 3(8): 1-7.
- Ganapathyselvam, G. and K. Sivakumar 2014. Phycosynthesis of silver nanoparticles and photocatalytic degradations of methyl orange dye using silver (Ag) nanoparticles synthesized from *Hypnea musciformis* (Wulf). J.V. Lamouroux. *Appl. Nanosci.* DOI:10.1007/S13204-014-0356-8.
- Henglein, A. 1993. Physicochemical properties of small metal particles in solution: "microelectrode" reactions, chemisorptions, composite metal particles, and the atom-to-metal transition. *J. Phys. Chem.*, 97: 5457-5471.
- Huang, J., Q. Li, D. Sun, L. Lu, Y. Su, X. Yang, H. Wang, Y. Wang, W. Shao, N. He, J. Hong and C. Chen 2007. Biosynthesis of silver and gold nanoparticles by novel sun dried *Cinnamomum camphora* leaf. *Nanotechnology*, 18: 104-105.
- Hutchison, J.E. 2008. Greener nanoscience: A proactive approach to advancing applications and reducing implications of nanotechnology. *ACS Nano.*, 2: 395-402.
- Kathiresan, K. and N. Asmathunisha 2013. A review on biosynthesis of nanoparticles by marine organisms. *Colloids Surf B*, 103:283-287.
- Kuber, C.B. and S.F. D'Souza 2006. Extracellular biosynthesis of silver nanoparticles using the fungus *Aspergillus fumigates*. *Colloids Surf B Interface*, 47: 160-164.
- Kumar, P., S. Senthamil Selvi, A. Lakshmi Praba, K. Prem Kumar, R.S. Ganeshkumar and M. Govindaraju 2012. Synthesis of silver nanoparticles from *Sargassum tenerimum* and screening phytochemicals for its anti-bacterial activity. *Nano. Biomed. Eng.*, 4: 12-16.
- Lengke, M.F., M.E. Fleet and G. Southam 2007. Biosynthesis of silver nanoparticles by filamentous cyanobacteria from silver (I) nitrate complex. *Langmuir*, 23: 2694-2699.
- Mansoori, G.A. 2005. Principles of Nanotechnology—Molecular-Based Study of condensed Matter in Small Systems, World Scientific Pub. Co., Hackensack, NJ.
- Mulvaney, P. 1996. Surface plasmon spectroscopy of nanosized metal particles. *Langmuir*, 12: 788-800.
- Nabikhan, A., K. Kandasamy, A. Raj and N.M. Alikunhi 2010. Synthesis of antimicrobial silver nanoparticles by callus and leaf extracts from salt marsh plants, *Sesuvium portulacastrum* L. *Colloids Surf B Interface*, 79: 488-493.
- Parashar, V., R. Parashar, B. Sharma and A.C. Pandey 2009. Parthenium leaf extract mediated synthesis of silver nanoparticles: a novel approach towards weed utilization. *Digestion J. Nanomaterials and Biostructures*, 4: 45-50.
- Satyavani, K., S. Gurudeeban, T. Ramanathan and T. Balasubramanian 2011. Biomedical potential of silver nanoparticles synthesized from calli cells of *Citrullus colocynthis* (L.). *J. Nanobiotechnology*, 9: 43-50.
- Swanson, 1953. Tatge, Natl. Bur. Stand. (U.S.), *Circ* Vol. 539, No. 1, 23.
- Udayasoorian, C., R. Vinoth Kumar and M. Jayabalakrishnan 2011. Extracellular synthesis of silver nanoparticles using leaf extract of *Cassia auriculata*. *Dig. J. Nanomater. Bios.*, 6(1): 279-283.
- Vigneshwaran, N., N.M. Ashtapature, P.V. Varadharajan, R.P. Nachane, K.M. Paralikar and R.H. Balasubramanya 2007. Biological synthesis of silver nanoparticles using the fungus *Aspergillus flavus*. *Materials Letters*, 61: 1413-1418.
- Yang, J.I., C.C. Yeh, J.C. Lee, S.C. Yi, H.W. Huang, C.N. Tseng and H.W. Chang 2012. Aqueous extracts of the edible *Gracilaria tenuistipitata* are protective against H<sub>2</sub>O<sub>2</sub>-induced DNA damage, growth inhibition and cell cycle arrest. *Molecules*, 17: 7241-7254.